



PRODUCT DATA

DYNACOAT™ H2O
Water Reducible Alkyd
Enamel 54-series

modified alkyd

PRODUCT DESCRIPTION
TYPICAL USES
PRODUCT ADVANTAGES
COLORS
GLOSS
PHYSICAL CONSTANTS
APPLICATION
SHIPPING & STORAGE

A high quality, quick drying, high gloss, water reducible coating for use on properly prepared ferrous metal. Lead and chromate free. Low VOC.

For industrial and commercial use including machinery, piping, structural steel, trailers, industrial compactors and containers, implements and plant equipment. Offers excellent protection of structural steel in light to moderately corrosive environments.

DYNACOAT™ H2O W/R ENAMEL offers excellent protection in exposures including mild industrial and marine environments. Exhibits very good adhesion to properly prepared ferrous metals. Fast drying with good recoatability and water resistance. Low VOC.

Black, White and several Safety and Equipment Colors available from stock. Special colors available subject to minimum order

High Gloss

Nonvolatile - By weight - 30.0 ± 2.0%
 By volume - 24.0 ± 1.0%

VOC (Calculated) - 3.41 lbs./gal.
 (without water) 408 grams/liter

Flash Point - 110°F (Setaflash)

Weight per gallon - 8.7 ± 0.2 lbs.

NOTE: Figures will vary according to color

Recommended Film Thickness - 1.5 mils dry, 6.3 mils wet

Theoretical Coverage @ 1.5 mils dry - 257 sq. ft./gal.

Method - Conventional or airless spray

Thinner - water

Dry time @ 75°F -

To touch	-	30 minutes
Tack free	-	1 hour
Dry Hard	-	8 hours

Consists of - 1 Gallon Unit 5 Gallon Unit

Unit Shipping Weight 9 lbs. 46 lbs.

Shelf Life - 6 months minimum from date of manufacture when maintained in protected storage @ 40-100°F (subject to reinspection thereafter).

APPLICATION INSTRUCTIONS

Consult your Mobile Paint Representative for the protective coating system best suited for your requirements.

Limitations: Apply in good weather when air and surface temperature are above 50°F and surface temperature is at least 5°F above the dew point. For optimum application properties, material should be between 70 to 100°F prior to mixing and application. Maintain unmixed material in closed containers in protected storage at 40 - 100°F. Do not apply to uncured wood or masonry. May be applied to damp but not wet surfaces. Do not apply in direct sun or on hot surfaces.

New or Unfinished Surfaces: Ferrous metal: For best performance, application to abrasive blasted surface is recommended. "Commercial Blast Cleaning" (SSPC-SP6) is recommended as the minimum for blast cleaning. Proper blast media and blasting equipment shall be used to produce an average profile depth of 1.5 mils minimum. Do not reuse abrasive media. Remove blasting dust and grit from surfaces before painting. Blasted surfaces should be coated within 8 hours after blasting or before rusting or other contamination of the surface occurs. If blasting is not possible, use "Hand or Power Tool Cleaning: (SSPC-SP2 or -SP3). **Galvanized metal:** Remove oil with mineral spirits. **Aluminum:** Etching with a phosphoric acid pretreatment solution is recommended for maximum adhesion. Clean all contamination by scrubbing with a mixture of household detergent and water or other effective means. Rinse clean with water and allow to dry.

Previously Painted Surfaces: Repair all damaged areas. Remove gloss from previous paint by sanding or "Brush Blasting" (SSPC-SP7) Remove rust, corrosion products, heavy chalk and loose or peeling paint by "Hand or Power Tool Cleaning" (SSPC-SP2 or -SP3). Spot prime any bare areas as required. If doubt exists concerning compatibility of this coating with the previous system, apply coating to a representative area (25 square feet minimum) and allow to cure and age several weeks. Then inspect for adhesion failure, wrinkling, lifting, blistering or any other sign of incompatibility. If there are no signs, coating work can proceed.

Tinting: Do not tint.

Mixing: This is a one component coating. Always mix thoroughly with a power agitator before application.

Thinning: This product is supplied at normal brushing viscosity. If thinning is necessary, thin up to 1/2 pint per gallon with water.

Application: Apply by brush, roller or conventional or airless spray. Roller application may require special care to prevent bubbling and more than one coat to obtain proper film thickness. Apply at 6.3 mils wet film thickness which will yield 1.5 mils dry film thickness.

Equipment: Brush - Use a good quality nylon brush. Roller - All purpose, good quality roller with 3/8" nap maximum. Conventional spray - For suction feed, use DeVilbiss MBC gun with E tip and needle and 30 air cap or equivalent at 40-45 psi atomizing pressure. For pressure feed, use DeVilbiss MBC gun with E tip and needle and 704 air cap or equivalent at 40-45 psi atomizing pressure and 5-8 psi fluid pressure, 3/8" ID material hose, double regulated pressure tank with oil and moisture separator. Airless Spray - Minimum of 28:1 ratio pump, .013"-.015" orifice tip, 1/4" ID material hose.

Cleanup: Clean all equipment immediately after use with warm, soapy water. Completely flush all spray equipment with this solution. Occasional flushing of spray equipment during the course of the working day helps prevent buildup and possible clogging. Final flushing of spray equipment with mineral spirits will prevent corrosion.

Safety: Safe storage, handling and use dictate that adequate health and safety precautions be observed with this product and any recommended thinners. User is specifically directed to consult the current Material Safety Data Sheet for this product as well as precautions contained on product labeling.

Notice: The technical data contained herein are true and accurate to the best of our knowledge. All products are offered and sold subject to Mobile Paint Manufacturing Company's Standard Conditions of Sale. Published technical data and instructions are subject to change without prior notice.

54DynacoatH2O (9/04)

LIMITED WARRANTY

The successful performance of this product is highly dependent on many factors beyond our control. Results are highly dependent upon the skill of the operator. This product is manufactured to meet the highest level of consistency and quality for the intended use. Mobile Paint warrants that its products meet the specifications which it sets for them. Should this product be proven to be off-specification within one year from date of shipment, Mobile Paint will, at its sole discretion, either replace the product or issue credit for the original purchase price of the product. The replacement or refund shall be the buyer's sole remedy and Mobile Paint and its affiliates **MAKE NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, DESIGN COMPATIBILITY AND FITNESS FOR A PARTICULAR PURPOSE. LABOR OR COST OF LABOR AND OTHER INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.