

PAINTER'S CHOICE Interior PVA Latex Primer White 619-6

PRODUCT DESCRIPTION

An quality, easy to apply flat latex primer to meet the requirements of professional painting contractors and apartment or condominium managers. Low VOC. Lead, mercury and chromate free.

TYPICAL USES

For residential and commercial use as a primer for interior walls and ceilings of properly prepared drywall, plaster, metal and masonry. For use in homes, offices, institutions, apartments and condominiums. Excellent for use as a primer/sealer for finish coats of latex or alkyd on interior walls and ceilings.

PRODUCT ADVANTAGES

Interior PVA Latex Primer has excellent adhesion and flexibility. Can be topcoated with latex or alkyd coatings. Fast drying, low odor and easy application. Lead, mercury and chromate free. Low VOC.

COLORS White

GLOSS Flat

PHYSICAL CONSTANTS

VOC (Calculated) 0.4 lbs./gal

50 grams per liter

Flash Point >250°F Setaflash Weight per gallon 11.3 + 0.2lbs

Nonvolatile By weight $-48.0 \pm 1.0\%$

By volume - 31.0 ± 1.0%

APPLICATION

Recommended Film Thickness - 1.5 mils dry, 4.8 mils wet Theoretical Coverage @1.2 mils dry - 332 sq/ ft/gal. Method - Brush, roll, conventional airless spray.

Thinner - Water

Dry time@ 75°F - To touch - 30 minutes

To handle - 1 hour To recoat - 2 hours

SHIPPING & STORAGE

Consists of - 1 Gallon unit 5 Gallon Unit

Unit Shipping Weight - 12lbs. 60lbs.

Shelf Life - 12 Months minimum from date of manufacture when maintained in protected storage 40-100°F (subject to reinspection thereafter).

APPLICATION INSTRUCTIONS

Consult your Mobile Paint Representative for the protective coating system best suited for your requirements.

Limitations: Apply in good weather when air and surface temperature are above 50°F and surface temperature is at least 5°F above the dew point. For optimum application properties, material should be between 70 to 100°F prior to mixing and application. Maintain unmixed material in closed containers in protected storage at 40-100°F. Not recommended for priming ferrous metal surfaces. Do not use as a finish coat.

Surface Preparation: Good surface preparation is essential to a satisfactory coating system. Surfaces to be coated should be clean and dry. Remove all dirt, dust, oil, grease, mildew, rust, loose or cracked paint or other contamination. Refer to label warning concerning sanding of previous coatings.

New or Unfinished Surfaces: Ferrous Metal: Remove rust. Primer with Rus-Kil Primer 10-series. Galvanized Metal: Remove oil with mineral spirits. Masonry: Must be fully cured, dry and clean. Allow a minimum of 30 days cure time before coating. Porous concrete should be coated with Block Filler 260-55. Hardboard: Caulk joints and cracks and allow caulk to dry thoroughly before painting. Drywall: Spackle drywall as needed and allow to dry thoroughly. Sand spackled areas smooth and remove dust prior to priming. Plaster: New plaster must be fully cured and dry. Old plaster must be hard and in good condition. Repair as necessary and allow to cure properly.

Previously Painted Surfaces: Repair all damaged areas. Remove loose and badly cracked paint by wire brushing, scraping, sanding or other method to provide a sound surface. Sand smooth all rough areas and feather edge areas of peeled coatings. Remove gloss from previous coatings by sanding. Spot prime all bare areas. If doubt exists concerning compatibility of this coating with the previous system, apply coating to a representative area (25 square feet minimum) and allow to cure and age several weeks. Then inspect for adhesion failure, wrinkling, lifting, blistering or any other sign of incompatibility. If there are no signs, coating work can proceed.

Tinting: May be tinted with up to 4 ounces per gallon of COLOR STUDIO colorant.

Mixing: This is a one component coating. Always mix thoroughly with a power agitator before application.

Thinning: This product is supplied at normal brushing viscosity. If thinning is necessary thin up to 1/2 pint per gallon with water.

Application: Apply by brush, roller or conventional or airless spray. Roller application may require special care to prevent bubbling and more than one coat to obtain proper film thickness. Apply at 4.8 mils wet film thickness which will yield 1.5 mils dry film thickness.

Equipment: Brush - Use a good quality nylon brush. Roller - All purpose, good quality roller with 3/8" nap maximum. Conventional spray - For suction feed, use DeVilbiss MBC gun with E tip and needle and 30 air cap or equivalent at 40-45 psi atomizing pressure. For pressure feed, use DeVilbiss MBC gun with E tip and needle and 704 air cap or equivalent at 40-45 psi atomizing pressure and 5-8 psi fluid pressure, 3/8" ID material hose, double regulated pressure tank with oil and moisture separator. Airless Spray - Minimum of 28:1 ratio pump, .013"-.015" orifice tip, 1/4" ID material hose.

Cleanup: Clean all equipment immediately after use with warm, soapy water. Completely flush all spray equipment with this solution. Occasional flushing of spray equipment during the course of the working day helps prevent buildup and possible clogging. Final flushing of spray equipment with mineral spirits will prevent corrosion.

Safety: Safe storage, handling and use dictate that adequate health and safety precautions be observed with this product and any recommended thinners. User is specifically directed to consult the current Material Safety Data Sheet for this product as well as precautions contained on product labeling.

Notice: The technical data contained herein are true and accurate to the best of our knowledge. All products are offered and sold subject to Mobile Paint Manufacturing Company's Standard Conditions of Sale. Published technical data and instructions are subject to change without prior notice.

619-6(2021)

LIMITED WARRANTY