



WEATHER-TITE®
Waterproofing Sealer, Clear
74-7

PRODUCT DESCRIPTION	
TYPICAL USES	
PRODUCT ADVANTAGES	
COLORS	
GLOSS	
PHYSICAL CONSTANTS	
APPLICATION	
SHIPPING & STORAGE	

A transparent, paintable waterproofing sealer. Provided as a ready-to-use solution which contains no silicones.

For industrial, commercial and residential use to provide a penetrating transparent water seal on most porous surfaces such as masonry, concrete, concrete block, brick, stucco, wood, canvas and fabric.

WEATHER-TITE® Waterproofing Sealer prevents water penetration while allowing the treated surface to breathe. May be painted over with oil or latex paints after proper drying. Contains no silicones. Low odor and easy to apply. Lead and chromate free.

Transparent

N/A

Nonvolatile - By weight - 6.0 ± 1.0%
VOC (Calculated) - 6.14 lbs./gal.
(excluding water) 733 grams/liter
Flash Point - 105°F (Setaflash)
Weight per gallon - 6.5 lbs ± 0.2 lbs.

Recommended Film Thickness - Material is for application to porous surfaces and film thickness can not be accurately measured.

Theoretical Coverage - 100-150 sq. ft./gal.

Method - Brush, roll or low pressure airless spray.

Thinner - MoPaxOI® 75-1 or mineral spirits.

Dry time @ 75°F - Allow 24 hours before recoating or topcoating.

Consists of -	1 Gallon Unit	5 Gallon Unit
Unit Shipping Weight	8 lbs.	36 lbs.

Shelf Life - 12 months minimum from date of manufacture when maintained in protected storage @ 40-100°F (subject to reinspection thereafter).

APPLICATION INSTRUCTIONS

Consult your Mobile Paint Representative for the protective coating system best suited for your requirements.

Limitations: Apply in good weather when air and surface temperature are above 50°F and surface temperature is at least 5°F above the dew point. For optimum application properties, material should be between 70 to 100°F prior to mixing and application. Maintain unmixed material in closed containers in protected storage at 40 - 100°F.

Should not be applied below grade or where hydrostatic pressure is present. Synthetic fibers should be tested to determine compatibility with this product prior to application. Do not use on rubber, plastic or asphalt.

Surface Preparation: Good surface preparation is essential to a satisfactory coating system. Surfaces to be coated should be clean and dry. Remove all dirt, dust, oil, grease or other contamination by solvent or detergent cleaning or other effective methods. All cutting, gluing, sanding, etc. should be done prior to application. Substrate must be **thoroughly** dry. This product will not penetrate damp surfaces and will create white spots. **Concrete Block:** Must be clean, dry and thoroughly cured. Remove loose mortar by scraping, wire brushing or other effective methods. **Concrete:** Must be fully cured, dry and clean. Allow a minimum of 30 days cure time before coating.

Previously Painted Surfaces: The material should be applied to unpainted surfaces only. Remove all traces of previous coatings before applying this coating.

Tinting: Do not tint.

Mixing: This is a one component coating. Stir thoroughly before use.

Thinning: Do not thin.

Application: Apply by brush, roller or low pressure airless spray. Apply until the surface is well saturated. Apply at a spreading rate of 100 to 150 square feet per gallon on more porous surfaces and 150 to 200 square feet per gallon on more dense surfaces such as brick and stucco.

Topcoating: High quality latex paints have been tested with excellent results over properly cured surfaces treated with WEATHER-TITE® Waterproofing Sealer. Allow sealer to dry a minimum of 24 hours before topcoating. Some latex paints may show difficulty in spreading over treated surfaces. May also be topcoated with oil or alkyd based paints.

Equipment: Brush - Use a good quality, stiff synthetic brush. Roller - All purpose, good quality roller with 3/4" nap maximum. Spray - May be applied with conventional "garden-type" sprayer or with airless spray equipment operated at low pressure. Care should be exercised to avoid over-atomization.

Cleanup: Clean all equipment immediately after use with MoPaxOI® 75-1 or mineral spirits. Completely flush all spray equipment with either of these solvents. Occasional flushing of spray equipment during the course of the working day helps prevent buildup and possible clogging.

Safety: Safe storage, handling and use dictate that adequate health and safety precautions be observed with this product and any recommended thinners. User is specifically directed to consult the current Material Safety Data Sheet for this product as well as precautions contained on product labeling.

74-7 (11/03)

LIMITED WARRANTY

The successful performance of this product is highly dependent on many factors beyond our control. Results are highly dependent upon the skill of the operator. This product is manufactured to meet the highest level of consistency and quality for the intended use. Mobile Paint warrants that its products meet the specifications which it sets for them. Should this product be proven to be off-specification within one year from date of shipment, Mobile Paint will, at its sole discretion, either replace the product or issue credit for the original purchase price of the product. The replacement or refund shall be the buyer's sole remedy and Mobile Paint and its affiliates **MAKE NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, DESIGN COMPATIBILITY AND FITNESS FOR A PARTICULAR PURPOSE. LABOR OR COST OF LABOR AND OTHER INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.