

PRODUCT DATA

Miracryl HS Activator 9000-930

Aliphatic Polyisocyanate

PRODUCT DESCRIPTION

TYPICAL USES

PRODUCT ADVANTAGES

COLORS

GLOSS

PHYSICAL CONSTANTS

APPLICATION

SHIPPING & STORAGE

A special blend of polyisocyanate resins in solvent. Low VOC and no HAPs.

Designed for use as an activator (hardener) for Miracryl HS Acrylic Enamel and other alkyd enamels, acrylic enamels and modified alkyd enamels. DO NOT use in enamels containing anticorrosive pigments, alcohol, water, or ether solvents.

Improves properties such as color and gloss retention, hardness, and dry time when used in selected acrylic and alkyd enamels. Offers improved temperature resistance in silicone containing coatings. May be added in the range of 10-20% by volume before thinning. Low VOC and no HAPs (Hazardous Air Pollutants).

Clear

Not Applicable

Nonvolatile - By weight - $75.0 \pm 2.0\%$

By volume - $70.0 \pm 1.0\%$

VOC (Calculated) - 2.2 lbs./gal.

266 grams/liter

Flash Point - 81°F (Setaflash) Weight per gallon - 8.85 ± 0.2 lbs.

Pot Life - Four hours minimum @ 75°F **Dry Time -** Dependent upon enamel used

Consists of -Half Gallon1 GallonUnit Shipping Weight5 lbs.10 lbs.

Shelf Life - 6 months minimum from date of manufacture when maintained in protected storage @ 40-100°F (subject to reinspection thereafter).

LIMITEDWARRANTY

The successful performance of this product is highly dependent on many factors beyond our control. Results are highly dependent upon the skill of the operator. This product is manufactured to meet the highest level of consistency and quality for the intended use. Mobile Paint warrants that its products meet the specifications which it sets for them. Should this product be proven to be off-specification within one year from date of shipment, Mobile Paint will, at its sole discretion, either replace the product or issue credit for the original purchase price of the product. The replacement or refund shall be the buyer's sole remedy and Mobile Paint and its affiliates MAKE NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, DESIGN COMPATIBILITY AND FITNESS FOR A PARTICULAR PURPOSE. LABOR OR COST OF LABOR AND OTHER INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.